


PRODUCT TYPE	NAME	10/07/2014
glazed ceramic & glazed porcelain	CLASSIC <i>series</i>	
TECHNICAL SPECIFICATION		


Technical Features

- glazed ceramic
- 8 colours
- 2 surfaces: gloss & satin (limited to selected colours only)
- 1 tile size


Colour



Amber




Antique White



Fluorite



Grey




Nero / Black



Onyx



Red



White

Format

Wall



10x30

MANUFACTURER	DISTRIBUTOR	Page
 <small>Close to you worldwide</small>	Prestige Tiles P/L 16 Raglan Road Auburn NSW 2144 p 8717 9044 f 8717 9017 www.prestigetiles.com	1

PRODUCT TYPE	NAME	10/07/2014
glazed ceramic & glazed porcelain	CLASSIC <i>series</i>	
TECHNICAL SPECIFICATION		



R.A.K. CERAMICS

MODEL: CLASSIC
 NOMINAL SIZE: 10 x 30 cm
 THICKNESS: 8.5 mm
 REF. STANDARD: ISO 13006: 2012

TYPE OF PRODUCT: GRES PORCELLANATO TILE
 NATURE OF SURFACE: GLAZED
 BODY GROUP: BIII

TEST DESCRIPTION	STANDARD TEST METHOD	STANDARD REQUIREMENTS ISO 13006: EN 14411	R.A.K. CERAMICS SPECIFICATION
LENGTH & WIDTH	BS EN ISO 10545-2	±0.5 %	±0.4 %
THICKNESS	BS EN ISO 10545-2	±10 %	±5 %
STRAIGHTNESS OF SIDES	BS EN ISO 10545-2	±0.3 %	±0.3 %
RECTANGULARITY	BS EN ISO 10545-2	±0.5 %	±0.4 %
CENTER CURVATURE	BS EN ISO 10545-2	±0.5 % -0.3 %	±0.3 %
EDGE CURVATURE	BS EN ISO 10545-2	±0.5 % -0.3 %	±0.3 %
WARPAGE	BS EN ISO 10545-2	±0.5 %	±0.3 %
WATER ABSORPTION	BS EN ISO 10545-3	$10 \% < E_b \leq 20 \%$	$10 \% < E_b \leq 18 \%$
MODULUS OF RUPTURE	BS EN ISO 10545-4	$\geq 12 \text{ N/mm}^2$	$\geq 18 \text{ N/mm}^2$
BREAKING STRENGTH	BS EN ISO 10545-4	$\geq 600 \text{ N}$	$\geq 650 \text{ N}$
RESISTANCE TO SURFACE ABRASION	BS EN ISO 10545-7	Manufacturer to state abrasion class	PEI Class 2
COEFFICIENT OF LINEAR THERMAL EXPANSION	BS EN ISO 10545-8	Test method available	$\leq 7 \times 10^{-6} / ^\circ\text{C}$
THERMAL SHOCK RESISTANCE	BS EN ISO 10545-9	Test method available	No visible defect
CRAZING RESISTANCE	BS EN ISO 10545-11	Required	No Crazing
RESISTANCE TO HOUSEHOLD CHEMICALS & SWIMMING POOL SALTS	BS EN ISO 10545-13	Minimum GB	Class GA No visible effect
RESISTANCE TO LOW CONCENTRATIONS ACIDS & ALKALIS	BS EN ISO 10545-13	Test method available	Class GLA No visible effect
RESISTANCE TO STAINING	BS EN ISO 10545-14	Minimum Class 3	Min. Class 4 Stain removed

MANUFACTURER	DISTRIBUTOR	Page
	Prestige Tiles P/L 16 Raglan Road Auburn NSW 2144 p 8717 9044 f 8717 9017 www.prestigetiles.com	2